

# Ampatop® Seal

Weldable roof membrane



- Weldable with solvent bonding and heat
- Both sides are processed, no waste
- Cutting and orientation aid
- Monolithic TPU technology
- For low roof pitches

Technical details		Value	Standard
s <sub>d</sub> value		0,2m	EN ISO 12572
Weight		350 g/m <sup>2</sup>	EN ISO 9073-2
Fire behaviour		E	EN 13 501-1
Tear resistance	longitudinal	350 N/5 cm	EN 12 311-2/A
	transverse	380 N/5 cm	
Reißdehnung	longitudinal	50 %	EN 12 311-2/A
	transverse	70 %	
Resistance to further tearing (nail shaft)	longitudinal	250	EN 12 310-1
	transverse	240	
Temperature resistance		-40° C – +100° C	
Resistance to water penetration		W1	EN 1928
Outdoor weathering		3 months	
Minimum roof slope		5°	
CE marking		EN 13859-1:2014	



## Forms of delivery

Article number	Description	Roll dimensions	Content of pallets
7640115534385	Ampatop® Seal 1,5 m	1.5 m × 30 m = 45 m <sup>2</sup>	30 rolls = 1'350 m <sup>2</sup>
7640115535665	Ampatop® Seal 3 m	3 m × 20 m = 60 m <sup>2</sup>	30 rolls = 1'800 m <sup>2</sup>
7640115534897	Ampatop® Seal Jumbo 1,5 m	1.5 m × 400 m = 600 m <sup>2</sup>	1 rolls = 600 m <sup>2</sup>
7640115535689	Ampatop® Seal Jumbo 3 m	3 m × 400 m = 1'200 m <sup>2</sup>	1 Rolle = 1'200 m <sup>2</sup>



Application videos



ISO 9001  
Swiss Research